

FUNCTIONAL EXPLORE

- Suitable for all indications

• Physical Characteristics

Density after sintering	$\geq 6.0\text{g}/\text{cm}^3$
CTE(25-500°C)	$(10.5 \pm 1.0) \times 10^{-6}\text{K}^{-1}$
Accelerated aging surface monoclinic phase content	<5%
Chemical solubility after sintering	<100 $\mu\text{g}/\text{cm}^2$
Radioactivity	<0.1Bq/g
Sintering temperature	1430-1550°C recommend 1480°C

• Chemical Composition

$\text{ZrO}_2 + \text{HfO}_2 + \text{Y}_2\text{O}_3$	>96.5%
Y_2O_3	5.8%-9.7%
Al_2O_3	<0.5%
Fe_2O_3	<0.5%
Er_2O_3	<2.0%
Others oxides	<0.5%

Light 1027MPa 46.6% $4.3\text{MPa} \cdot \text{m}^{1/2}$

